

SERIES	711	712	747	750	751	752	784	786	792
SYSTEM	S 1C	S 1C	UV	S 2C	S 2C	S	S 2C	S 2C	S 2C
ABS / SAN	★		★	★ H	★ H	★ (H)	★ H	★ H	
Acrylics (PMMA)	★		★	★ H	★ H	★ (H)	★ H	★ H	
Duroplastics			★	★ H	★ H	★ (H)	★ H	★ H	
Glass & Ceramic			★	★ H	★ H				
Laquered surfaces	★		★	★ H	★ H	★ (H)	★ H	★ H	★ H
Metal			☆	★ H	★ H	☆ (H)	★ H	★ H	
PET-A	★		★			★ (H)	★ H	★ H	
PET-G						★ (H)			
Polyamid (PA)			★	★ H	★ H	★ (H)	★ H	★ H	
Polycarbonate (PC)	★		★	★ H	★ H	★ (H)	★ H	★ H	
Polyester	☆		☆	★ H	★ H	★ (H)	★ H	★ H	
Polyethylene (PE)			★🔥	★🔥H	★🔥H	★🔥(H)	★🔥H	★🔥H	
Polyoxymethylene				★ H	★ H				
(POM) Polypropylene		★	★🔥	★🔥H	★🔥H	★🔥(H)	★🔥H	★🔥H	
(PP) Polystyrole (PS)	★		★			★ (H)	★ H	★ H	
PVC, rigid	★		★	★ H	★ H	★ (H)	★ H	★ H	
PVC, soft	★		★			★ (H)			
TPE / Rubber									★ H
Tritan™ (Copolyester)							★ H	★ H	

INDEX S= Solvent WB= Water based UV= UV curing ★= suitable ☆= Inspection necessary H= Hardener (H)= Also 1C processable 🔥= only after pre-treatment

More detailed information is contained in the technical data sheet (<https://www.decotechgroup.com/consumables/sds>)